


TEST REPORT

Adomast Manufacturing Ltd
Barkston Road
Carlton Industrial Estate
Barnsley
S71 3HU



White
Rose
Laboratory
Services
Ltd

Lumley St • Castleford • WF10 5LB
01977 520625 • enquiries@whiteroselabs.co.uk

Report WRL/16/1955psd
Issue date 06/10/16

Material	14mm chippings	Sample N°	S/16/1955
Site	Not stated	Sampled by	Client
Specification	-	Date sampled	03/10/16
Source	Adomast Manufacturing Ltd	Date received	05/10/16
Supplier	Rebound	Date tested	06/10/16
Sample location	Not stated	Date reported	06/10/16
Sample type	Bulk		
Order number	20161003.01R		

BS EN 933-1 2012 Determination of particle size distribution, sieving method

Analysed by dry seiving

Sieve Size	Amount passing
mm	%
31.5	100
25	99
20	99
16	94
14	90
12.5	78
10	49
8	21
6.3	5
4	0
0.063	0.0

A handwritten signature in black ink, appearing to read 'J Church'.

J Church
Managing Director