



Planning

Civil
Engineering
Consultancy

Site
Investigation

Specialist
Testing

Sports
Surface
Advice

Project
Management

www.sportslabs.co.uk

LABORATORY PERFORMANCE REPORT

In accordance with

BS EN 1177:2008 – Determination of Critical Fall Height*

Sample Reference PlaySafe Rubber Chippings

Report Number 17571/3631

Report Status Final

Issue Date 22/09/2016

Client **Adomast Manufacturing Ltd**
Barkston Road
Carlton Industrial Estate
Barnsley
S71 3HU
England

FOREWORD

1. This report has been prepared by Sports Labs limited with all reasonable skill, care and diligence within the terms of the contract with the Client and within the limitations of the resources devoted to it.
2. This report is confidential to the Client and Sports Labs Limited accepts no responsibility whatsoever to third parties to whom this report, or any part thereof, is made known. Any such party relies upon the report at their own risk.
3. This report shall not be used for engineering or contractual purposes unless signed by the Author and the Checker and unless the report status is "Final".



HEAD OFFICE

Sports Labs Ltd
1 Adams Square,
Brucefield Industry Park
Livingston
EH54 9DE

Tel: +44(0)1506 444 755
Email: info@sportslabs.co.uk

REGIONAL LOCATIONS

Johannesburg
Ghent
Ankara
Boston & Seattle
Casablanca

Registered in
Scotland No 186755



1.0 INTRODUCTION

We refer to the sample 'PlaySafe Rubber Chippings' delivered to our Laboratory. The client requested testing to be carried out in accordance with the requirements of BS EN 1177:2008 - Determination of Critical Fall Height.

Prepared By Craig Melrose
Laboratory Supervisor
22/09/2016


.....

Checked By Sean Ramsay
Laboratory Director
22/09/2016


.....

TEST DETAILS	
System Name	PlaySafe Rubber Chippings
Test Condition	As delivered
Surface Temperature (°C)	24.8 °C
Air Temperature (°C)	22.7 °C
Relative Humidity (%)	58 %
Fixing Method	Self Weighted
Substrate	Concrete
Shockpad type	n/a
Total Depth (cm)	5 cm
Infill Type	100% recycled rubber products
Infill moisture content at test (%)	0.2 %



2.0 TEST DETAILS

- 2.1 The test Specimen was prepared in accordance with the manufacturer's instructions.
- 2.2 The specimens were tested in the conditions and temperatures described in BS EN 1177: 2008 to the loose particulate method.

3.0 TESTING

- 3.1 Determination of Critical Fall Height – BS EN 1177: 2008


4.0 TEST RESULTS

- 4.1 Detailed test results are given overleaf in tabular and graphical format.



5.0 HIC (Critical Fall Height) Test Results


Test Results	Drop Test 1			Drop Test 2		
	Drop Height (m)	$T_2 - T_1$	HIC	Drop Height (m)	$T_2 - T_1$	HIC
	0.395	20	87	0.523	25	111
	0.411	25	89	0.532	21	274
0.416	17	149	0.536	14	315	
Test Results	Drop Test 3			Drop Test 4		
	Drop Height (m)	$T_2 - T_1$	HIC	Drop Height (m)	$T_2 - T_1$	HIC
	0.668	19	192	1.030	15	541
	0.684	17	561	1.046	16	593
	0.684	17	1681	1.058	7	3705



Calculated Critical Fall Height Value	0.6 m
--	--------------




Time signal response graph.



Surface photograph



6.0 Test Locations



End of Report